

03 30 00	Cast-in-Place Concrete
03 37 13	Shotcrete
03 40 00	Precast Concrete
03 70 00	Mass Concrete

# MasterFiber<sup>®</sup> MAC 100 Plus

## Macrosynthetic Fiber

### Description

MasterFiber MAC 100 Plus product, a macrosynthetic fiber, is manufactured from a proprietary blend of polypropylene resins, in compliance with ASTM C 1116/C 1116M “Standard Specification for Fiber-Reinforced Concrete.”

MasterFiber MAC 100 Plus product also conforms to the requirements of CSA B66-10 “Design, material, and manufacturing requirements for prefabricated septic tanks and sewage holding tanks”.

### Applications

Recommended for use in:

- Industrial and warehouse floors
- Commercial slab construction
- Concrete pavement
- White topping and overlays
- Thin wall precast
- Shotcrete
- Septic Tanks
- Composite metal decks

### Features

MasterFiber MAC 100 Plus product is specifically engineered for use as shrinkage and temperature (secondary) reinforcement and provides excellent plastic shrinkage control and reduced settlement cracking. MasterFiber MAC 100 Plus product has the following features:

- Uniform distribution throughout the concrete matrix
- Excellent finishability
- Excellent post-first crack performance

### Benefits

- Eliminates the need for welded-wire reinforcement (WWR) and conventional steel bars as secondary reinforcement, depending on the application
- Effective tight crack control
- Provides excellent plastic shrinkage crack reduction and settlement control
- Improves green strengths – permits earlier stripping of forms with less rejection
- Reduces construction time and overall labor and material costs
- Increases flexural toughness, impact and shatter resistance

### Performance Characteristics

#### Physical Properties

Specific Gravity	0.91
Melting Point	320 °F (160 °C)
Ignition Point	1,094 °F (590 °C)
Absorption	Nil
Alkali Resistance	Excellent
Tensile Strength	75,000 psi (515 MPa)
Length	1.5 in. (38 mm)
Aspect Ratio	59
Chemical Resistance	Excellent

## Guidelines for Use

**Dosage:** The recommended dosage for MasterFiber MAC 100 Plus product is 3 lb/yd<sup>3</sup> (1.8 kg/m<sup>3</sup>). It can be used at dosage rates from 3 lb/yd<sup>3</sup> (1.8 kg/m<sup>3</sup>) up to 13 lb/yd<sup>3</sup> (7.8 kg/m<sup>3</sup>) or the equivalent dosage of 0.2% to 0.9% by volume, unless otherwise specified.

For composite metal deck applications, minimum dosage is 4 lb/yd<sup>3</sup> (2.4 kg/m<sup>3</sup>) as recommended by the Steel Deck Institute.

**Mixing:** MasterFiber MAC 100 Plus product is packaged in pre-weighed, ready-to-use, degradable bags which are designed to be introduced at any time before or during mixing of concrete produced in accordance with procedures specified in ASTM C 94/C 94M.

## Engineering Specifications

MasterFiber MAC 100 Plus product, when used at an appropriate dosage, is an option for the replacement of WWR, as a safe and easy-to-use reinforcing system that is rust proof, alkali resistant, and compliant with Industry codes when used in concrete mixed in accordance with ASTM C 94/C 94M.

MasterFiber MAC 100 Plus product should be specified for use in concrete slabs:

- For enhanced residual strength, toughness and durability
- To reduce plastic shrinkage cracking
- To increase abrasion resistance
- To improve impact resistance
- To reduce permeability

Master Builders Solutions does not recommend the fiber for use in slabs as a replacement for any structural steel reinforcement.

MasterFiber MAC 100 Plus product at a dosage of 3.0 kg/m<sup>3</sup> (5.0 lb/yd<sup>3</sup>) also conforms to the requirements of CSA B66-10 "Design, material, and manufacturing requirements for prefabricated septic tanks and sewage holding tanks."

## Storage and Handling

**Storage Temperature:** MasterFiber MAC 100 Plus product should be stored at temperatures below 140 °F (60 °C). Avoid storing near strong oxidizers and avoid sources of ignition. Use caution when stacking to avoid unstable conditions. Store in a sprinkled warehouse.

## Packaging

MasterFiber MAC 100 Plus product is packaged in pre-weighed degradable 3 lb (1.36 kg), 4 lb (1.81 kg) and 5 lb (2.27 kg) bags that can be added directly to the mixing system.

## Related Documents

Safety Data Sheets: MasterFiber MAC 100 Plus product

## Additional Information

For additional information on MasterFiber MAC 100 Plus product, contact your local sales representative.

*Master Builders Solutions, a brand of MBCC Group, is a global leader of innovative chemistry systems and formulations for construction, maintenance, repair and restoration of structures. The Admixture Systems business provides advanced products, solutions and expertise that improve durability, water resistance, energy efficiency, safety, sustainability and aesthetics of concrete structures, above and below ground, helping customers to achieve reduced operating costs, improved efficiency and enhanced finished products.*

*Utilizing worldwide resources, the Master Builders Solutions community of experts are passionate about providing solutions to challenges within all stages of construction, as well as the life cycle of a structure. At Master Builders Solutions we create sustainable solutions for construction around the globe.*

## Limited Warranty Notice

Master Builders Solutions warrants this product to be free from manufacturing defects and to meet the technical properties on the current Technical Data Guide, if used as directed within shelf life. Satisfactory results depend not only on quality products but also upon many factors beyond our control. MASTER BUILDERS SOLUTIONS MAKES NO OTHER WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, INCLUDING WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE WITH RESPECT TO ITS PRODUCTS. The sole and exclusive remedy of Purchaser for any claim concerning this product, including but not limited to, claims alleging breach of warranty, negligence, strict liability or otherwise, is shipment to purchaser of product equal to the amount of product that fails to meet this warranty or refund of the original purchase price of product that fails to meet this warranty, at the sole option of Master Builders Solutions. Any claims concerning this product must be received in writing within one (1) year from the date of shipment and any claims not presented within that period are waived by Purchaser. MASTER BUILDERS SOLUTIONS WILL NOT BE RESPONSIBLE FOR ANY SPECIAL, INCIDENTAL, CONSEQUENTIAL (INCLUDING LOST PROFITS) OR PUNITIVE DAMAGES OF ANY KIND.

Purchaser must determine the suitability of the products for the intended use and assumes all risks and liabilities in connection therewith. This information and all further technical advice are based on Master Builders Solutions' present knowledge and experience. However, Master Builders Solutions assumes no liability for providing such information and advice including the extent to which such information and advice may relate to existing third party intellectual property rights, especially patent rights, nor shall any legal relationship be created by or arise from the provision of such information and advice. Master Builders Solutions reserves the right to make any changes according to technological progress or further developments. The Purchaser of the Product(s) must test the product(s) for suitability for the intended application and purpose before proceeding with a full application of the product(s). Performance of the product described herein should be verified by testing and carried out by qualified experts.